

RESEARCH PAPER

Investigation On Abrasive Water Jet Machining of Al-Al₂O₃ MMC

Bhanudas Bachchhav

Received 22 March 2020; Revised 17 October 2020; Accepted 21 October 2020; © Iran University of Science and Technology 2021

ABSTRACT

The present work aims to investigate Abrasive Water Jet Machining parameters for machining of Al_2O_3 Metal Matrix Composite. Plan of experiments, based on Taguchi's analysis technique were performed using L_9 orthogonal array. A correlation was established between concentration of Al_2O_3 , Stand-off distance, pressure and Transverse feed with Metal Removal Rate, Surface Roughness, Overcut and Taper angle by regression analysis. On the basis of experimental results and S/N ratio analysis, ranking of the parameters has been done. The analysis of variance (ANOVA) has been used to find out the impact of individual parameters on response parameters. Al_2O_3 concentration plays a very significant role in determination of MRR and surface roughness. Also overcut is largely influenced by stand off distance. Furthermore, multi-objective optimization can be carried out using advanced optimization techniques. This work helped to generate technical database for industrial applications of MMC.

KEYWORDS: *Al-Al*₂*O*₃ *MMC; AWJM; Taguchi method; MRR; Surface roughness; Taper; Over-cut.*

1. Introduction

Aluminium based metal matrix composites (MMC) are widely used in variety of applications such as aerospace and automotive sectors due to their excellent mechanical, physical properties and high strength to weight ratio. Now a days, machining of MMC to high quality, better accuracies and surface finish draws attention in manufacturing industries. Presence of hard abrasive reinforcement particles influence largely on tool life, cutting forces, mechanism of formation of chips, machinability and associated cost in conventional machining [1]. Arun Kumar et al. used the Taguchi's design of experiments (DOE) for the optimization of the process parameters to minimize the surface roughness and maximizing the material removal rate using WEDM. Phate et. al. (2019) has been tried machining of Al/SiCp MMC by wire cut electrical discharge machining (WEDM) process [3]. However; it was observed that Metal Removal Rate (MRR) in EDM and WEDM process is very low and also due to hard and nonconducting abrasive particles make it difficult to

Corresponding author: Bhanudas Bachchhav bdbachchhav@aissmscoe.com machine due to braking of wire in between [2-3]. In order to get maximum Material Removal Rate (MRR) and better surface finish Abrasive Water Jet Machining (AWJM) is being extensively used in many industrial applications.

AWJM is a hybrid machining process makes use of both abrasive jet and water jet. It is used for machining of wide variety of materials irrespective of their hardness. Extensive research reviews from the inception to the current developments in Abrasive Water jet Machining have been done [4-9]. Korat and Acharya (2014) research related reviewed to improving performance measures, optimization of process variables and monitoring and control of AWJM process [5]. A wide range of AWJM industrial applications for materials having different hardness and mechanical properties are also reported [5, 7]. AWJM removes material from the work-piece by striking high pressure jet of water mixed with abrasive particles. Issues relating to Kerf width and drag at high pressure, stand off distance and feed rate needs to be addressed particularly for larger thickness of materials [10-11]. Inaccuracies such as noncircularity and taper were observed in deep hole drilling operations [12]. Wang [13] investigated negative effect on the depth of cut due to nozzle oscillation and improper selection of cutting parameters. Nozzle travel speed and higher water

^{1.} HeadDepartment of Mechanical EngineeringAll India Shri Shivaji Memorial Society's College of Engineering.

pressure has lager impacts on kerf angle and kerf width [14]. Sadhikumar et. al. optimized the process parameters while machining aluminium composites by AWJM and observed that minimum Kerf angle and good surface finish can be achieved at higher water pressure, less standoff distance and low transverse speed [15]. Santhanukumar et. al., [16] while machining Al/SiC/Al₂O₃ composites using AWJM found that the process parameters such as stand-off distance, traverse speed, water pressure and abrasive flow rate have significant effect on striation angle and striation zone length. Wear mechanism while machining Si₃N₄, AlN and ZrB₂ were identified and found wear characterized mainly due to micro-cutting, plastic deformation and erosion [17].

effect of abrasive water-jet process An parameters while machining AA631-T6 allovs were investigated by using various optimization techniques such as genetic algorithm, bee colony, simulated annealing, grey fuzzy logic, fire fly algorithm, particle swarm optimization etc. [18]. An impact of technological factors such as abrasive mass flow rate, abrasive mesh, traverse cutting speed and rotating speed of an alloy Monel K-500 while machining with hydroabrasive process were analyzed and found that traverse speed of cutting head and abrasive mass flow rate has most significant effect in order to determine material removal rate [19]. Ravi Kumar et. Al., investigated an effect of stand-off distance, transverse distance and percentage of tungsten carbide on MRR and surface roughness using multi response optimization model and set optimum process parameters [20]. Alberdi et. al. [21] was evaluated machinability index for two different CFRP composite materials with two different thicknesses machinability model were developed. According to them, the machinability index of different composite materials varies differently [21]. They found that composite materials have а significantly higher

machinability index than that of metals particularly while machining with abrasive water jet [21].

Still machine manufacturers do not have good databases for machining of newly developed composite materials. It is required to generate database through extensive experimental investigations. It has been witnesses that very little research has been carried out on AWJM of metal matrix composites [20]. Also majority of the investigations are limited to the Metal Removal Rate (MRR) and Surface roughness (SR). Hardly any work pertaining to the other inaccuracies produced during machining by AWJM has been addressed so far. The aim of present work is to investigate an effect of process parameters of AWJM on metal removal rate (MRR), surface roughness and accuracies like amount of over-cut and taper.

2. Materials and Methods

2.1. Preparation of work piece

Metal Matrix Composites (MMC) is composed of a metallic matrix (Aluminium) and a dispersed ceramic (Oxides) phase. In this work Al 2124 is used as a matrix and Al₂O₃ ceramics as a filler material. In Stir Casting liquid state MMC manufacturing method. discontinuous reinforcement is stirred into molten metal which is allowed to solidify. By mechanical stirring a dispersed phase is mixed with a molten matrix metal. Figure 1 shows a stir casting process. Powder reinforcement is distributed into molten metal by means of mechanical stirring process. The production of MMC using this process can affect by process variables such as holding temperature, stirring speed, size of impeller and position of impeller in the melt which has impact on mechanical properties. The properties of MMC are strongly depending on the interfacial bonding strength of reinforcement and matrix phase.



Fig. 1. Stir casting principle

A plate of size 130 mm x 80 mm x 10 mm were cast of Al- Al_2O_3 MMC and finished using on vertical milling machine to brought of cast. Hardness was measured with the Brinell hardness test according for all three plates and found that 73.48 BHN, 76.73 BHN and 78.21 BHN for 10 %, 20 % and 30 % concentration of Al_2O_3 in MMC respectively, this depicts that addition of Al_2O_3 increases hardness.

2.2. Experimental setup

Experiments were conducted on CNC Mach 2B Abrasive water jet machine. Fig. 2 shows schematic of Abrasive Water Jet Machine which removes material from the surface by erosion of fine-grained abrasive particles striking the surface at a high velocity.



Fig. 2. Schematic of abrasive water jet machine

It is contains reservoir/water tratement plant which is used for storing water. The water is pumped from the reservoir. High pressure intensifier pumps are used to pressurize the water. For the abrasive water jet, the operating pressure capacity of 40,000 PSI HP. At this high pressure the flow rate of the water is reduced greatly. Intensifier is connected to the pump that pressurizes water from the pump to a desired level. Accumulator is used for temporarily storing the pressurized water. It is connected to the flow regulator through a control valve which controls the direction and pressure of pressurized water that is to be supplied to the nozzle. Flow regulator is used to regulate the flow of water. Nozzle renders the pressurized water and abrasives to the work-piece to get desired shape.

2.3. Plan of experiments

Taguchi's design of experiments was used with L_9 Orthogonal Array at 3 levels and 4 factors. Independent parameters are Concentration of Al_2O_3 , Stand-off distance, Pressure and Transverse speed. The levels of various process parameters are as shown in Table 1. There are four response parameters i.e. Material removal rate (MRR), Surface roughness (Ra), Overcut (mm) and Taper (degrees).

Investigation on Abrasive Water Jet Machining of Al-Al₂O₃MMC

Tab. 1. l	Process	paramete	ers and the	eir levels			
Deremoto	ra	Levels					
Faramete	15	Level 1	Level 2	Level 3			
Conc. of Al ₂ O	3 (%) C	10	20	30			
Stand-off Dist	t. (mm)	2	4	6			
SD							
Pressure (MPa) P	240	310	380			
Transverse	Feed	305	310	315			
(mm/rev) F							

3. Results and Discussion

3.1. Analysis for metal removal rate

Material removal rate (MRR) is calculated in mm^3/min by using Eq. 1.

MRR

```
= Total volumn removed from the workpiece
```

Time taken

Eq. (1)

Using MINITAB, Taguchi Design Software, S/N ratios for MRR, ranking of parameters and ANOVA are calculated. Experimental results, Ranking of Parameters and ANOVA analysis are shown in Table 2, Table 3 and Table 4 respectively. Here, Delta denotes proportionate change in S/N ratio.

R U N	С %	SD mm	P MPa	F mm/ min	M (mm ³ /r	RR nin×10 ³	MRR (mm/ min)	S/N ratio
IN				111111	a	b	10^3 Mean	
1	10	2	240	305	4.5	4.5	4.50	13.06
2	10	4	310	310	4.6	4.6	4.60	13.25
3	10	6	380	315	4.8	4.9	4.85	13.71
4	20	2	310	315	3.3	3.3	3.30	10.37
5	20	4	380	305	3.5	3.4	3.45	10.75
6	20	6	240	310	3.3	3.4	3.35	10.49
7	30	2	380	310	3.2	3.2	3.20	10.10
8	30	4	240	305	2.5	2.4	2.45	7.77
9	30	6	310	315	3.2	3.2	3.20	10.10

Tab. 2. Experimental results for MRR

Tab. 3. Response table for signal to noise ratios

Level	Conc. Of Al ₂ O ₃	Stand Off Distance	Pressure	Transverse Feed
1	13.344	11.179	10.447	11.307
2	10.541	10.596	11.243	11.285
3	9.328	11.438	11.523	10.621
Delta	4.016	0.843	1.077	0.686
Rank	1	3	2	4

Here in machining operation the metal removal rate is desired to be larger, hence larger S/N ratio as a better condition is considered as an objective function. The main effects plot for the S/N ratios is plotted for the various parameters namely Concentration of Al_2O_3 , Stand off Distance,

Pressure and Transverse Feed are shown in Fig. 3. From Table 3, the material removal rate is mainly influenced by conc. of Al_2O_3 followed by pressure; stand off distance and transverse feed. Increase in conc. of Al_2O_3 decreases MRR due to its high hardness.



Fig. 3. Main effect plot for S/N ratios (MRR)

Source	DF	Adj SS	Adj MS	F-Value	P-Value
Regression	4	4.65208	1.16302	9.12	0.027
Conc. of Al2O3	1	4.33500	4.33500	33.99	0.004
Stand Off Dist.	1	0.02667	0.02667	0.21	0.671
Pressure	1	0.24000	0.24000	1.88	0.242
Transverse Feed	1	0.05042	0.05042	0.40	0.564
Error	4	0.51014	0.12753		
Total	8	5.16222			

Tab. 4. Analysis of variance for MRR

Mathematical model for MRR in terms of additive concentration of Al_2O_3 , Stand off distance, Pressure and Transverse speed were obtained from regression analysis using MINITAB19 statistical software. The Eq. (2) obtained was as follows:

 $MRR = 10.02 - 0.0850 \text{ Conc. of } Al_2O_3 + 0.0333 \text{ Stand Off Distance} + 0.00286 \text{ Pressure} - 0.0183 \text{ Transverse Feed}$ Eq. (2)

Where, S = 0.357120, R-sq. 90.12 % and R-sq (adj)= 80.24%

As the R^2 value of regression analysis is more than 70 %, the choice of the process parameters and results obtained seems to be consistent.

3.2. Analysis for surface roughness

Surface roughness (Ra) was measured in μ m using digital surface roughness tester Mitutoyo SJ-201 with a cut-off length of 0.8 mm. Experimental results, Ranking of Parameters and ANOVA analysis foe surface roughness are shown in Table 5, Table 6 and Table 7 respectively. Here, Delta denotes proportionate change in S/N ratio.

R	С	SD	Р	F	Sur	Surface		S/N
U	%	mm	MPa	mm	Rough	ness ^(µm)	Mean	ratio
Ν				/min				
					а	b		
1	10	2	240	305	4.88	4.96	4.92	-13.83
2	10	4	310	310	3.76	3.66	3.71	-11.38
3	10	6	380	315	2.29	3.14	2.15	-08.78
4	20	2	310	315	5.20	5.21	5.20	-14.32
5	20	4	380	305	5.58	5.55	5.56	-14.90
6	20	6	240	310	5.67	5.69	5.68	-15.08
7	30	2	380	310	5.93	5.93	5.93	-15.46
8	30	4	240	305	6.22	6.35	6.28	-15.96
9	30	6	310	315	5.34	5.34	5.34	-14.55

Tab. 5. Experimental results for surface roughness

Τa	Tab. 6. Response table for signal to noise ratios (SR)								
Level	Conc. of	Stand Off	Pressure	Transverse Feed					
	Al_2O_3	Dist.							
1	-11.34	-14.54	-14.96	-14.43					
2	-14.77	-14.09	-13.42	-13.98					
3	-15.33	-12.81	-13.05	-13.03					
Delta	3.99	1.74	1.91	1.41					
Rank	1	3	2	4					





Fig. 4. Main effect plot for S/N ratios (Surface Roughness)

Here in machining operation surface roughness is desired to be smaller, hence smaller is better is considered as an objective function. The main effects plot for the S/N ratios is plotted for the various parameters namely Concentration of Al_2O_3 , Stand off Distance, Pressure and Transverse Feed are shown in Fig. 4.

From Table 6, the surface roughness is mainly influenced by conc. of Al_2O_3 followed by pressure; stand off distance and transverse feed. Table 7 depicts Analysis of variance for surface roughness.

Source	DF	Adj SS	Adj MS	F- Value	P- Value
Regression	4	8.9544	2.2386	6.49	0.049
Conc. of Al ₂ O ₃	1	6.4274	6.4274	18.64	0.012
Stand Off Dist.	1	0.8971	0.8971	2.60	0.182
Pressure	1	1.1926	1.1926	3.46	0.136
Transverse	1	0.4374	0.4374	1.27	0.323
Feed					
Error	4	1.3791	0.3448		
Total	8	10.3335			

Tab. 7. Analysis of variance for Surface Roughness

As increase in conc. of Al_2O_3 increases surface roughness as hard and brittle particles of Al_2O_3 are dislodged from the ductile aluminium . Surface roughness decreases with increase in stand off distance, pressure and transverse feed Eq. (3).

Surface	= 22.5 + 0.1035 Conc. of Al ₂ O ₃	-
Roughness	0.193 Stand Off Dist.	-
	0.00637 Pressure-	
	0.0540 Transverse Feed	
	Eq. (3)

Where, S = 0.587169, R-sq.= 86.65 %. As the R² value of regression analysis is more than 70 %, the choice of the process parameters and results obtained seems to be consistent.

3.3. Analysis for over-cut

An over-cut was measured by using Mitutoyo non contact type optical profile projector having

Protractor screen size of 300mm with projection lenses of 50x and 100x magnification. Experimental results are shown in Table 8.

Tab. 8. Experimental results for overcut									
R	С	SD	Р	F	Over-	cut ^(mm)	OC	S/N	
U	%	mm	MP	mm		h	Mean	ratio	
Ν			а	/mim	а	D			
1	10	2	240	305	0.36	0.41	0.38	8.272	
2	10	4	310	310	0.44	0.41	0.42	7.426	
3	10	6	380	315	0.57	0.56	0.56	4.958	
4	20	2	310	315	0.41	0.48	0.44	7.006	
5	20	4	380	305	0.56	0.53	0.54	5.268	
6	20	6	240	310	0.99	1.00	0.99	0.043	
7	30	2	380	310	0.57	0.56	0.56	4.958	
8	30	4	240	305	0.67	0.70	0.68	3.284	
9	30	6	310	315	0.71	0.81	0.76	2.364	

Table 8 shows experimental results. In this, an over-cut is inaccuracy hence an objective smaller is better is considered to calculate mean square deviation and signal to noise ratios.

Table 9 depicts the ranking of the parameters based on S/N ratios. Over-cut is largely influenced by Stand off Distance followed by Conc. of Al_2O_3 , Pressure and transverse feed.

	Tab. 9. Re	sponse tabl	e for over-	cut
Laval	Conc. Of	Stand of	Drogguro	Transverse
Level	Al_2O_3	Dist.	Plessure	Feed
1	6.886	6.746	3.867	5.302
2	4.106	5.327	5.599	4.143
3	3.536	2.456	5.062	5.083
Delta	3.350	4.290	1.733	1.159
Rank	2	1	3	4

Fig. 5 depicts the main effects plot for the S/N ratios plotted for the various parameters namely Concentration of Al_2O_3 , Stand off Distance, Pressure and Transverse Feed.



Fig. 5. Main effect plot for S/N ratios (Over-cut)

Table 10 depicts Analysis of variance for an over-cut. From an Eq. (4), Overcut increases with increase in Conc. of Al_2O_3 , Stand off distance and Transverse Feed and decresases with

pressure. As stand off distance increases, the atmospheric drag leading to spread up water jet causing oversize.

Investigation on Abrasive Water Jet Machining of Al-Al₂O₃MMC

Tab. 10	. An	alysis of v	ariance fo	r over-c	cut	
Source	DE	14:55	A di MS	F	Р	
Source	DF	Auj 55	Auj MS	Value	Value	
Regression	4	0.235163	0.058791	3.92	0.107	
Conc. of Al_2O_3	1	0.067204	0.067204	4.48	0.102	
Stand of Dist.	1	0.142604	0.142604	9.52	0.037	
Pressure	1	0.025350	0.025350	1.69	0.263	
Transverse	1	0.000004	0.000004	0.00	0.987	
Feed						
Error	4	0.059937	0.014984			
Total	8	0.295100				
						_

Over-cut = 0.31 + 0.01058 Conc. of Al₂O₃ + 0.0771 Stand of Dist.

0.000929 Pressure

+ 0.00017 Transverse Feed

Eq. (4)

Where, S= 0.1224, R-sq.= 79.69 %

As the R^2 value of regression analysis is more than 70 %, the choice of the process parameters and results obtained seems to be consistent.

3.4. Analysis for taper

By using optical profile projector the diameter from top and bottom surface was measured. Plate thickness is 10 mm. Accordingly taper angle was calculated using Equation (5).

Taper angle (α) = $tan^{-1}(D - d/2l)$ Eq. (5)

Where, D, d is diameter measured on profile projector from top and bottom surface, l is total thickness of plate i.e. 10 mm.

Table 11 shows experimental results with an objective function of smaller is better to calculate MSD and S/N ratio. Two replicates were taken. From table 12, ranking of the parameters were done. Concentration of Al₂O₃ contributes largely to produce taper in hole drilling. As Al₂O₃ concentration increases, chipping of hard abrasive may cause increase in diameter at one end than the other, followed by stand off Pressure. distance, Transverse feed and

		Tab	. 11. Exp	periment	al resul	ts for t	aper	
R	С	SD	Р	F Mm	Taper	angle	Taper	S/N
U	%	mm	MPa	/min	(deg	(ree)	Angle	ratio
Ν					а	b	Mean	
1	10	2	240	305	0.20	0.22	0.21	13.54
2	10	4	310	310	0.23	0.25	0.24	12.38
3	10	6	380	315	0.28	0.32	0.30	10.43
4	20	2	310	315	0.54	0.53	0.53	5.43
5	20	4	380	305	1.30	1.54	1.42	-3.07
6	20	6	240	310	1.91	1.86	1.88	-5.50
7	30	2	380	310	0.50	0.71	0.60	4.23
8	30	4	240	305	0.63	0.81	0.72	2.78
9	30	6	310	315	2.34	2.30	2.32	-7.31

Level	Conc. Of Al ₂ O ₃	Stand off Dist.	Pressure	Transverse Feed
1	12.1241	7.7381	3.6083	1.0530
2	-1.0504	4.0325	3.5036	3.7058
3	-0.0960	-0.7929	3.8659	6.2190
Delta	13.1745	8.5310	0.3623	5.1660
Rank	1	2	4	3



Fig. 6. Main effect plot for S/N ratios (Taper)

Tab. 13. Analysis of variance for taper							
Source	DF	Adj SS	Adj MS	F	Р		
			-	Value	Value		
Regression	4	4.05186	1.01297	5.57	0.062		
Conc. of Al ₂ O ₃	1	1.39684	1.39684	7.68	0.050		
Stand off Dist.	1	1.65900	1.65900	9.12	0.039		
Pressure	1	0.04002	0.04002	0.22	0.663		
Transverse Feed	1	0.95600	0.95600	5.26	0.084		
Error	4	0.72749	0.18187				
Total	8	4.77935					

Eq. (6)

Taper = 24.0 + 0.0482 Conc. of Al₂O₃ + 0.2629 Stand off Dist.

+ 0.2029 Stand of 0.00117 Pressure

- 0.0798 Transverse Feed

.0/98 Transverse ree

Where S= 0.426464, R-sq=84.75 %

From R-sq value the results obtained are found to be consistent.

4. Conclusions

In the present work the effect of AWJM parameters on the Al- Al₂O₃ metal matrix composites were carried out using Taguchi analysis. An effect of Conc. of Al₂O₃, Stand off distance, Pressure and Transverse Feed on metal removal rate, surface roughness, over-cut and amount of taper was investigated. Parameters were ranks based on S/N ratio and it was observed that for MRR and surface roughness ranking is same as Conc. of Al₂O₃ followed by Pressure, Stand off distance and Transverse Feed; however for overcut and taper stand of distance is influencing more. Empirical relationship between and parameters under consideration and response variables were established by using regression analysis. The adopted model has good adequacy at 95% confidence level. Cracks, brittle fracture were witnesses along the surface of the composites.

The presented work can be extended to optimize the parameters for better MRR and reduced inaccuracies. Furthermore, multi-objective optimization can be carried out using recent optimization techniques.

Thus the presented approach will help the industry to have technical database for the use of AWJM for aluminium based MMC.

5. Acknowledgement

The authors would like to acknowledge Kakade Laser, Narhe, Pune, Maharashtra, India-51 for providing the overall support for the completion of this work.

References

- Anthony, X. M., Ajit Kumar, *"Machinability of Hybrid Metal Matrix Composite- A Review."*, Procedia Engineering, Vol. 174, (2017), pp. 1110-1118.
- [2] Vinod, K.,Vikas, K., Kamal, J., " An experimental analysis and optimization of machining rate and surface characteristics in WEDM of Monel-400 using RSM and desirability approach." Journal of Industrial Engineering International. Vol. 11, (2015), pp. 297-307.

- [3] Phate, M., Toney, S., Phate, V., "Optimization Performance Parameters of OHNS Die Steel Using Dimentionless Analysis Intergrated with Desirability Function" International Journal of Industrial Engineering and Production Research. Vol. 30, (2019), pp. 11-23.
- [4] Shah, R. V., Patel, D. M., "Abrasive Water Jet Machining: The Review", International Journal of Engineering Research and Applications, Vol. 2, No. 5, (2012), pp. 803-806.
- [5] Korat, M. M., Acharya G. D., "A Review on Current Research and Development in Abrasive Waterjet Machining", International Journal of Engineering Research and Applications, Vol. 4, No. 1, (2014), pp. 423-432.
- [6] Batra, T., Devilal, "Literature Review on Abrasive Jet Machining". Int. Journal of Resaerch in Aeronautical and Mechanical Engineering, Vol. 3, No. 12, (2015), pp. 26.32.
- [7] Shrikant, D. V., Sreenivasa, R., "Abrasive Jet Machining- Research Review" Int. Journal of Advanced Engineering Technology, Vol. 5, No. 2, (2014), pp. 18-24.
- [8] Prasad, S. R., Ravindranath, K., Devakumar, M. L. S., "A Research review on Advanced Approaches in Abrasive Jet Machining" IOSR Journal of Mechanical and Civil Engineering, (2016), pp. 57-62.
- [9] Ramachandran, N., Ramkrishnan, N., "A Review of Abrasive Jet Machining", J. Mater. Process. Technol., Vol. 39, (1993), pp. 21-31.
- [10] Kantha, B., Krishnaiah, C. O. V., "A study on recycling of Abrasives in Abrasive Water Jet Machining" Wear, Vol. 254, pp. 763-773.
- [11] Doreswamy, D., Shivamurthy, B., Anjaiaj, D., Sharma, Y., "An Investigation of Abrasive Water Jet Machiningon Graphite/Glass/Epoxy Composite", Int. J. Manuf. Eng., (2015), pp. 1-11.
- [12] Kowsari, K., Nouraei, H., James, D. F., Spelt, J. K., Papini, M., "Abrasive Slurry Jet

Micro-machining of Holes in brittle and Ductile Materials" J. Mater. Process. Technol. Vol. 214, (2014), pp. 1909-1920.

- [13] Wang, J., "Predictive Depth of Jet Penetration Models for Abrasive Waterjet Cutting of Alumina Ceramics" Int. J. Mech, Sci. Vol. 49, No. 3, (2007), pp. 306-316.
- [14] Gupta, V., Pandey, P. M., Garg, M. P., Khanna, R., Batra, N. K., "Minimization of Kerf Taper Angle and Kerf Width using Taguchi's Method in Abrasive Water Jet Machining of Marble" Procedia. Mater. Sci. Vol. 6, (2014), pp. 140-149.
- [15] Sasikumar, K. S. K., Arulshri, K. P., Ponappa, K., Uthayakumar, M., "A Study on Kerf Characteristics of Hybrid Aluminuium 7075 Metal Matrix Composites Machined using Abrasive Water Jet Machining Technology", Proc IMechE Part B: J Engineering Manufacture, (2016), pp. 1-15.
- [16] Santhanakumar, M., Adalarasan, R., Rajmohan, M., "Parameter Design for Cut Surface Characterestics in Abrasive Water Jet Cutting of Al/SiC/Al₂O₃ Composite using Grey Theory Based RSM" J. Mech. Sci. Technol. Vol. 30, No. 1, (2016), pp. 371-379.
- [17] Senthil, K. S., Mathan, K. N., Lakshmi, A. K., "An Investigation of Abrasive and Erosion Behaviour of AA 2618 reinforces with Si₃N₄, AlN, ZrB₂ In Situ Composites by Using Optimization techniques", Arch. Civ. Mech. Eng. Vol. 17, (2017), pp. 43-54.
- [18] Rajkamal, S., Dinesh, S., "Experimentation Investigation of Abrasive Water Jet Machining Parameters Using Taguchi Evolutionary Optimization Techniques", Swarm and Evolutionary Computation, Vol. 32, (2017), pp. 167-183.
- [19] Ján, C., Sergej, H., Petr, H., Miroslav, G., Dagmar, K., František, B., Dušan, M., Dominika, L., "Hydro-abrasive disintegration of alloy Monel K-500 – the influence of technological and abrasive factors on the surface quality", Procedia Engineering, Vol. 149, (2016), pp. 17-23.
- [20] Ravi Kumar, K., Sreebalaji, V. S., Pridhar, T., "Characterization and Optimization of Abrasive Water Jet Machining Parameters of

102

Aluminium/Tugsten Carbide Composites" Measurement, (2017).

[21] Alberdia, A., Suáreza, A., Artazaa, T., Escobar-Palafoxb, G. A., Ridgwayb, K., "Composite Cutting with Abrasive Water Jet" Procedia Engineering, Vol. 63, (2003), pp. 421-429.

Follow This Article at The Following Site:

Bachchhav B. Investigation on Abrasive Water Jet Machining of Al-Al2O3 MMC. IJIEPR. 2021; 32 (1) :93-103 URL: http://ijiepr.iust.ac.ir/article-1-1038-en.html

